

Datasheet AS TEBMT32



- (1): Hardness rockwell: HRM.
(2): Hardness rockwell: HRC.
(3): Coefficient of friction dynamic: oil/grease.

Material	
Material	Bimetal

Availability	Unit	Value
Mating Axis	Hardness	> 48 ⁽²⁾
Mating Axis	Roughness	Ra=0.16-0.63
Min. inside diameter	mm	10
Max. inside diameter	mm	100
Length standard	mm	On request
Also available as flange bushing	DIN1494	

Metric Bushing		Wall Thickness	Outside Chamfer	Inner Chamfer
Type	AS TEBMT32	3	2±0.6	0.6±0.4
I.D.	35	3.5	2±0.6	0.6±0.4
High	39	4	2.5±0.6	0.6±0.4
		4.5	2.5±0.6	0.6±0.4

Flange Bushing		Wall Thickness	Outside Chamfer	Inner Chamfer
Type	AS TEBMT32F	2	1.2±0.4	0.6±0.3
I.D.	85			
High	89			

Physical Properties	Test Standard	Unit	Value
Density	ASTM D792	g/cm ³	-
Max. swell in water at 20 °C	ASTM D570	%	-

Mechanical Properties	Test Standard	Unit	Value
Compressive strength static	ASTM D695	MPa	130
Compressive strength dynamic	ASTM D695	MPa	-
Module of elasticity	ASTM D695	MPa	-
Tensile strength	ASTM D3410	MPa	-
Shear strength	ASTM D3410	MPa	-
Impact strength	ASTM D256	kJ/m ²	-
Hardness rockwell	ASTM D785	HRM/HRC	> 48 ⁽²⁾

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Kunststoffen B.V. is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Kunststoffen B.V. 2016 ©.

Thermal Properties	Test Standard	Unit	Value
Thermal expansion	ASTM D696	K	$19 \cdot 10^{-6} \text{K}^{-1}$
Min. working temperature		°C	-
Max. working temperature		°C	-
Intermittent working temperature		°C	-

Friction Properties	Test Standard	Unit	Value
Linear velocity grease lubricated		m/s	2.5
Linear velocity oil lubricated		m/s	10
Max. pv load grease lubricated		MPa*m/s	2.8
Max. pv load oil lubricated		MPa*m/s	10
Friction coefficient grease lubricated		μ	0.05-0.15
Friction coefficient oil lubricated		μ	-