

Datasheet AS TEBMT35



- (1): Hardness rockwell: HRM.
(2): Hardness rockwell: HRC.
(3): Coefficient of friction dynamic: oil/grease.

| Material | |
|----------|---------|
| Material | Bimetal |

| Availability | Unit | Value |
|----------------------------------|-----------|-------------------------|
| Mating Axis | Hardness | > 270 HB ⁽¹⁾ |
| Mating Axis | Roughness | Ra=0.16-0.63 |
| Min. inside diameter | mm | 10 |
| Max. inside diameter | mm | 100 |
| Length standard | mm | On request |
| Also available as flange bushing | DIN1494 | |

| Metric Bushing | | Wall Thickness | Outside Chamfer | Inner Chamfer |
|----------------|------------|----------------|-----------------|---------------|
| Type | AS TEBMT35 | 3 | 2±0.6 | 0.6±0.4 |
| I.D. | 35 | 3.5 | 2±0.6 | 0.6±0.4 |
| High | 39 | 4 | 2.5±0.6 | 0.6±0.4 |
| | | 4.5 | 2.5±0.6 | 0.6±0.4 |

| Flange Bushing | | Wall Thickness | Outside Chamfer | Inner Chamfer |
|----------------|-------------|----------------|-----------------|---------------|
| Type | AS TEBMT35F | 2 | 1.2±0.4 | 0.6±0.3 |
| I.D. | 85 | | | |
| High | 89 | | | |

| Physical Properties | Test Standard | Unit | Value |
|------------------------------|---------------|-------------------|-------|
| Density | ASTM D792 | g/cm ³ | - |
| Max. swell in water at 20 °C | ASTM D570 | % | - |

| Mechanical Properties | Test Standard | Unit | Value |
|------------------------------|---------------|-------------------|-------------------------|
| Compressive strength static | ASTM D695 | MPa | 120 |
| Compressive strength dynamic | ASTM D695 | MPa | - |
| Module of elasticity | ASTM D695 | MPa | - |
| Tensile strength | ASTM D3410 | MPa | - |
| Shear strength | ASTM D3410 | MPa | - |
| Impact strength | ASTM D256 | kJ/m ² | - |
| Hardness rockwell | ASTM D785 | HRM/HRC | > 270 HB ⁽¹⁾ |

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Kunststoffen B.V. is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Kunststoffen B.V. 2016 ©.

| Thermal Properties | Test Standard | Unit | Value |
|----------------------------------|---------------|------|----------------------------------|
| Thermal expansion | ASTM D696 | K | $19 \cdot 10^{-6} \text{K}^{-1}$ |
| Min. working temperature | | °C | - |
| Max. working temperature | | °C | - |
| Intermittent working temperature | | °C | - |

| Friction Properties | Test Standard | Unit | Value |
|--|---------------|---------|-----------|
| Linear velocity grease lubricated | | m/s | - |
| Linear velocity oil lubricated | | m/s | 15 |
| Max. pv load grease lubricated | | MPa*m/s | - |
| Max. pv load oil lubricated | | MPa*m/s | 8 |
| Friction coefficient grease lubricated | | μ | 0.06-0.17 |
| Friction coefficient oil lubricated | | μ | - |